

# No Ordinary<sup>®</sup> Medical Gloves

The No Ordinary<sup>®</sup> glove is manufactured by one of the largest plants in Thailand and distributed throughout Europe and the United Kingdom. This world-class 3.2g series medical examination glove is suited to the healthcare industries due to the high tensile strength and elasticity, complete testing for use with Chemotherapy drugs, and meeting the ISO, ASTM, and EN standards with FDA 510(k) and CE approvals.



## Multi-Purpose



## Technical Data Sheet EUK

<b>Material</b>	Nitrile, not made with natural rubber latex
<b>Type</b>	Powder Free, Examination Glove
<b>Specification</b>	Non-Sterile/Disposable/Ambidextrous
<b>Cuff</b>	Beaded
<b>Colour</b>	Blue
<b>Internal Surface</b>	Polymerised or Chlorinated
<b>External Surface</b>	Finger tip textured
<b>Primary</b>	Acrylonitrile Butadiene
<b>Packaging</b>	100 pcs/box – 10 boxes/carton

Size	Weight
<b>Small</b>	3.0g ± 0.3g
<b>Medium</b>	3.2g ± 0.3g
<b>Large</b>	3.6g ± 0.3g
<b>Extra-Large</b>	4.2g ± 0.3g

## Product Properties (Size Medium)

Test Method	Characteristics	Specifications
<b>ASTM D6319</b>	Width (mm)	95±10 95
	Length (mm)	≥240
	Thickness Single (mm) Finger	≥ 0.05
	Thickness Single (mm) Palm	≥ 0.05
<b>ASTM D515</b>	Freedom from holes	AQL 1.5
<b>ASTM D412</b>	Before accelerated ageing:	
	Tensile Strength (MPa)	≥ 14
	Ultimate elongation (%)	≥ 500
<b>ASTM D573</b>	After accelerated aging at (70±2°C 166±2 hr):	
	Tensile Strength (MPa)	≥ 14
	Ultimate elongation (%)	≥ 400
<b>ASTM D6124</b>	Powder Control (mg/glove)	≤2.0

## Chemotherapy Drug Permeation Resistance Tested

Chemical Tested	Avg. Time in mins
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	15.1
Cisplatin, 1.0 mg/ml (1,000 ppm)	>240
Cyclophosphamide (Cytosan), 20.0 mg/ml (20,000 ppm)	>240
Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm)	>240
Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm)	>240
Etoposide (Toposar), 20.0 mg/ml (20,000 ppm)	>240
Fluorouracil, 50.0 mg/ml (50,000 ppm)	>240
Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm)	>240
Vincristine Sulfate, 1.0 mg/ml (1,000 ppm)	>240
Mechlorethamine HCl, 1.0mg/ml (1,00 ppm)	>240
Methotrexate, 25.0mg/ml (25,000ppm)	>240
Mitomycin C, 0.5 mg/ml (500ppm)	>240
Thiotepa, 10.0 mg/ml (1,000 ppm)	15.1

## Certifications



## Product Standards

### US Regulatory Standards

<b>FDA 510(k)</b>	K172930
<b>ASTM D6319</b>	Physical Properties & Dimensions
<b>ASTM D6978</b>	Tested for Use with Chemotherapy Drugs
<b>ASTM F1671</b>	Viral Penetration
<b>21 CFR 177.2600</b>	Overall Migration, Food Contact

### EU Regulatory Standards

<b>EN 455-1,2,3,4</b>	Physical Properties & Dimensions
<b>EN 374-1,2,4,5</b>	Chemical & Micro-organism Permeation
<b>EN 1041:2008+A1:2013</b>	Protective Gloves General Requirements
<b>EN 388:2010</b>	Mechanical Standard
<b>EN 21420:2020</b>	EU PPE Glove Standards
<b>EN 16523-1:2015+A1:2018</b>	Chemical & Micro-organism Permeation
<b>EN 1186:2002</b>	Overall Migration, Food Contact
<b>Module B/Module C2</b>	EU Type Examination, CE 2777
<b>PPE Category III (EU) 2016/425</b>	EU Declaration of Conformity, Type B, CE 2777
<b>MDR 2017/745, Class I</b>	EU Medical Device Regulation, CE 0123

### Quality Standards

<b>ISO 13485:2016</b>	Quality Management Systems - MPSAP 708421
<b>ISO 9001:2015</b>	Quality Management Systems
<b>SA 8000:2014</b>	Manufacturing and Distribution Approval
<b>BSCI</b>	Social Compliance