

No Ordinary[®] Medical Gloves

The No Ordinary[®] glove is manufactured in Malaysia and distributed to North America. This world-class 3.5g series medical examination glove is suited to the healthcare industries due to the high tensile strength and elasticity, complete testing for use with Chemotherapy drugs, and meeting the ISO, ASTM, and EN standards with FDA 510(k) and CE approvals.



Multi-Purpose



Technical Data Sheet USA

| | |
|-------------------------|---|
| Material | Nitrile, not made with natural rubber latex |
| Type | Powder Free, Examination Glove |
| Specification | Non-Sterile/Disposable/Ambidextrous |
| Cuff | Beaded |
| Colour | Blue |
| Internal Surface | Chlorinated |
| External Surface | Fingertip textured |
| Primary | Nitrile |
| Packaging | 100 pcs/box – 10 boxes/carton |

| Size | Weight |
|--------------------|-------------|
| Small | 3.2g ± 0.3g |
| Medium | 3.5g ± 0.3g |
| Large | 4.0g ± 0.3g |
| Extra-Large | 4.5g ± 0.3g |

Product Properties (Size Medium)

| Test Method | Characteristics | Specifications |
|-------------------|---|----------------|
| ASTM D6319 | Width (mm) | 95±10 95 |
| | Length (mm) | ≥240 |
| | Thickness Single (mm) Finger | ≥ 0.05 |
| | Thickness Single (mm) Palm | ≥ 0.05 |
| ASTM D515 | Freedom from holes | AQL 2.5 |
| ASTM D412 | Before accelerated ageing: | |
| | Tensile Strength (MPa) | ≥ 14 |
| | Ultimate elongation (%) | ≥ 500 |
| ASTM D573 | After accelerated aging at (70±2°C 166±2 hr): | |
| | Tensile Strength (MPa) | ≥ 14 |
| | Ultimate elongation (%) | ≥ 400 |
| ASTM D6124 | Powder Control (mg/glove) | ≤2.0 |

Chemotherapy Drug Permeation Resistance Tested

| Chemical Tested | Avg. Time in mins |
|---|-------------------|
| Carmustine (BCNU), 3.3mg/ml (3,300 ppm) | 22.6 |
| Cisplatin, 1.0 mg/ml (1,000 ppm) | >240 |
| Cyclophosphamide (Cytosan), 20.0 mg/ml (20,000 ppm) | >240 |
| Dacarbazine (DTIC), 10.0 mg/ml (10,000 ppm) | >240 |
| Doxorubicin Hydrochloride, 2.0 mg/ml (2,000 ppm) | >240 |
| Etoposide (Toposar), 20.0 mg/ml (20,000 ppm) | >240 |
| Fluorouracil, 50.0 mg/ml (50,000 ppm) | >240 |
| Paclitaxel (Taxol), 6.0 mg/ml (6,000 ppm) | >240 |
| Vincristine Sulfate, 1.0 mg/ml (1,000 ppm) | >240 |
| Mechlorethamine HCl, 1.0mg/ml (1,00 ppm) | >240 |
| Methotrexate, 25.0mg/ml (25,000ppm) | >240 |
| Mitomycin C, 0.5 mg/ml (500ppm) | >240 |
| Thiotepa, 10.0 mg/ml (1,000 ppm) | 43.9 |

Certifications



Product Standards

| US Regulatory Standards | |
|-------------------------|--|
| FDA 510(k) | K211666 |
| ASTM D6319 | Physical Properties & Dimensions |
| ASTM D6978-05 | Tested for use with Chemotherapy Drugs |
| ASTM F1671 | Viral Testing |
| 21 CFR 177.2600 | Overall Migration, Food Contact |

| EU Regulatory Standards | |
|----------------------------|--------------------------------------|
| EN 455-1,2,3,4 | Physical Properties & Dimensions |
| EN 374-1,2,4,5 | Chemical & Micro-organism Permeation |
| EN 420:2003+A1:2009 | EU PPE Glove Standards |
| EN 16523-1:2015 | Chemical & Micro-organism Permeation |

| Quality Standards | |
|-----------------------|------------------------------|
| ISO 13485:2016 | Quality Management Systems |
| ISO 9001:2015 | Quality Management Systems |
| GMP | Good Manufacturing Practices |
| Sedex Approved | Social Compliance |